

# Solar PV Encapsulant

### **KNACK 360 POE**

It is a PID and snail trails resistance, UV and weather stable POE solar PV Encapsulant. It has wide process window, proven for glass to backsheet solar modules. It can be used for single stage as well as short cycle multi stage lamination processes





## **KNACK 360 POE**

### **PROPERTIES**

Particulars	Test Method	Unit	Values
Thickness	ASTM D 6988 - 21	mm	0.45 to 0.8 ± 5%
Width	Scale	mm	Up to 1400
Melting Point	ISO 11357 - 3	°C	70 ± 5
Surface type	Visual		Orange peel
Tensile Strength	ASTM D 882-18	MPa	12 ± 3
Elongation	ASTM D 882-18	%	≥500
Shore Hardness	ASTM D 2240-15	Shore - A	70 ± 5
Water Absorption	ISO 62 - 2008	%	≤0.1
Adhesion to Glass	ASTM D 903	N/cm	≥75
Adhesion to Back sheet	ASTM D 903	N/cm	≥75
Thermal Shrinkage	(160°C, 5 min. on Glass Plate)	%	≤2
Optical Transmittance	ASTM E 424	%	≥90
UV Cut Off Wavelength	ASTM E 424	nm	360 ± 30
Refractive Index	ISO 489		1.48
Dielectric Strength	ASTM D149	kV/mm	≥25
Volume Resistivity	IEC 62788-1-2	Ohm.cm	≥1x10 <sup>16</sup>
Gel Content	IEC 62788-1-6	%	≥70
Lamination Parameters	Single Stage	Double Stage (Stage 1)	Double Stage (Stage 2)
Evacuation Time (Minute)#	4 - 6	4 - 6	
Lamination Time (Minute)	8 - 15	2 - 4	6 - 9
Temperature (°C)*	145 - 165	145 - 165	145 - 165

<sup>\*</sup>Temperature and #Vacuum to be uniformly maintained across the laminator. #Vacuum to be applied at -760 mm Hg, Periodic calibration of the machine input parameters to be done by Machine user.

#### Packing:

- Length/Roll: 130/150meterNo. of Rolls/Pallet: 9/12
- Total Linear Meters/Pallet: 1560/1800
- Each roll is sealed in a protective bag in corrugated box
- Boxes are strapped on suitable pallets

#### **Storage Condition and Shelf Life:**

- Store in undamaged original packaging, temperature between 20°C-30°C and humidity between 40-60% RH
- Recommended use within 9 months from date of manufacture
- Consume within 12 hrs.
  once opened from original packing